

Table 4.3 Densities of block samples of unaltered, weakly and strongly supergene altered manganese

Zone	Unaltered			Weakly altered			Strongly altered				
	Rex16	Rex44	Rex85	Rex70	Rex71	Rex74	Rex2	Rex24	Rex16	Rex71	Rex74
V		3.46									
W		3.59									
X1		3.42							2.38		2.05
X2	3.16	3.71									2.67
X3	3.76	3.57				2.80					
Y	3.45	3.50	3.26	3.29		2.50				2.94	
Z	3.75	3.64	3.62	3.61		2.93				3.60	
M	3.78	3.66	3.68	3.49	3.48	3.10	3.11				
C	3.54	3.66	3.58		3.27	2.85	3.10	2.99			
N	3.58	3.60	3.67		3.48		3.06	2.97			
B	3.54	3.51	3.60		3.41		2.85	2.87			
L	3.52	3.59	3.50		3.27		3.10	3.22			

Note: Relative densities are in g/cm³



ore.

